

WW41
WATERBORNE LACQUER SYSTEMS FOR INTERIOR WOOD FURNITURE
Akvilac TIX 25 TCW 448 6909

The waterborne system WW41 is thixotropic lacquer system for different kind of wood furniture, panels, frames, doors, chairs etc. This system can be used as clear or with Akvi Color, Dicco Color or Dicco Lasyr stains.

Akvi Color is water-borne wood stain and tintable with Akvi Tone colorants. Dicco Color is solvent-borne wood stain which contains soluble light resistant dyestuff. Dicco Lasyr is semi-transparent wood stain and tintable with Temaspeed Premium colorants.

Akvilac Tix 25 TCW is thixotropic lacquer especially suitable for vertical spraying applications. The lacquer easy to spray and even 200 µm wet film thickness is possible to spray without sagging problems. The lacquer very suitable for door and chair manufactures. The lacquer film is very transparent and film clarity is very similar to solvent borne lacquers. Akvilac Tix 25 TCW lacquer fulfills R4 resistance requirements according IOS-MAT-0066 specification.

LACQUER SYSTEM WITH STAIN

	Product	Application method	Application
1 x staining	Akvi Color	Spraying	60–80 g/m ²
1 x priming	Akvilac Tix 25 TCW	Spraying	80–120 g/m ²
1 x top lacquering	Akvilac Tix 25 TCW	Spraying	80–120 g/m ²

PRODUCT PROPERTIES

Solid Content 31 volume-% (448 6909)

Specific gravity 1.0 kg/l (448 6909)

Application methods Spraying

Drying times

	80–120 g /m ²	+23°C	+50°C
Akvilac Tix 25	Dry to sand Dry to stack	15–45 min 2-4 h	5–15 min 1–2 h

Stacking temperature below +35°C.

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Thinner Water or Akvi Thinner

Gloss (DIN 67530, ISO 2813/60°) Semi-matt

Cleaning of equipment Water

Colours Clear. Akvi Color, Dicco Color or Dicco Lasyr stains can be used before lacquering.

SURFACE PREPARATION

Dirt, dust and other unfamiliar material must be removed from the surface. Wooden material should be sanded before application with sand paper 150–240 mesh. All sanding dust must be removed before application.

APPLICATION CONDITIONS

During application and drying the temperature of the air, paint and surface should be at least +18°C. The relative humidity should not exceed 70%. Good ventilation is needed during drying process.

APPLICATION

Stir Akvi Color stain carefully before application. Apply an even coat on the dry and clean surface and let it dry.

Stir Akvilac Tix 25 carefully before application. Thin the lacquer with water if necessary. Apply an even coat and let it dry about 30 min (in temperature of 20–30°C) before sanding.

Sand the surface carefully with sand paper 320 or 400 mesh and remove sanding dust before the second application. Apply an even coat and let it dry about 2–4 h (in temperature of 20–30°C temperature) before further processing.

The drying time depends of film thickness, temperature, relative humidity and the air ventilation.

Application with airless or conventional spraying system. Nozzle size is 0.009–0.013” and spraying distance from the object is about 20–25 cm.

MAINTENANCE LACQUERING

Wash down the surface with MAALIPESU detergent and rinse carefully with water. Remove old loose lacquer with scraper. Sand down surface and remove the sanding dust.

Stir Akvilac FD 25 TCW, Kiva Interior lacquer, Merit Jahti or Unica Super well before use. Apply evenly 1–2 thin coats of lacquer. Sand lightly after the first coat and remove sanding dust before the second application.

EKE17072014

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.